



MACRONIX INTERNATIONAL CO., LTD.

Product/Process Change Notice

PCN # P-2102-0006

Date: 2021/02/18

Dear Customer:

Please be informed that Macronix is going to add 2nd source assembly subcontractor to backup customer original approved assembly subcontractors for 8WS0N 8x6(3.4x4.3EP) package products. The 2nd source assembly subcontractor is LINGSEN.

The detailed information about this change is described in the following pages. This process change has passed Macronix' qualification based on JEDEC standard, and the qualification report is attached below.

If you have any questions, concerns, or requests about this change, please contact your local Macronix Sales Representatives within 30 days, otherwise Macronix will assume customer received the PCN with no comments and the change is acceptable to the customer. Macronix follows JEDEC J-STD-046, it stipulates: ".....Lack of acknowledgement of the PCN within 30 days constitutes acceptance of the change".

Thank you.

Macronix International Co., Ltd.

旺宏電子股份有限公司

(Note: For the customers who receive Macronix PCNs via distributors, Macronix will assist the distributors to convey the PCNs to the customers. It is each distributor's responsibility to communicate and track the responses of each customers and report back to Macronix, the distributor shall assume full responsibilities if failed to do so.)

PCN No.: P-2102-0006**Issue Date :** 2021/02/18**Subject:** Adding a new assembly vendor–LINGSEN for 8WSON 8x6(3.4x4.3EP) package products.**Affected Macronix Part No.:**

MX25U25645GZ4I00

MX25U25673GZ4I40

Package type: 8WSON 8x6(3.4x4.3EP) package products**Change Category :** New assembly vendor**Reason of Change:**

To increase 8WSON 8x6(3.4x4.3EP) package assembly capacity and flexibility.

Before Change :

Assembly vendor:

1. ASECL

After Change :

Assembly vendors:

1. ASECL
2. LINGSEN

Product identification:

ASECL assembled IC the marking has vendor code: X

LINGSEN assembled IC the marking has vendor code: L

Assessment of Change:

1. No impact to Form, Fit, Function, Quality & Reliability.
2. LINGSEN assembled 8WSON 8x6(3.4x4.3EP) package has passed Macronix' qualification based on JEDEC MSL level 3 standards, and it is also Halogen-Free, and meets the RoHS standards..
* Attached is LINGSEN assembled 8WSON 8x6(3.4x4.3EP) package qualification report.
3. LINGSEN has been one of Macronix' qualified assembly vendors with good quality for a long time.

Schedule:

Sample available date: 2021/3/15

1st shipping date: 2021/4/1 (Or follow PCN agreement with the customer)



LINGSEN 8L WSON (8x6x0.8 mm) Package Qualification Report

1. PURPOSE:

To qualify the new assembly subcontractor “LINGSEN” for 8L WSON (8x6x0.8 mm) package.

2. PACKAGE PROFILE:

ASSEMBLY HOUSE	LINGSEN
PACKAGE	8L WSON (8x6x0.8mm)
DIE SIZE	6434 x 4827 μm^2
DIE ATTACH	Nitto EM-700J
LEAD FRAME	Copper
WIRE BOND MATERIAL	Au
MOLD COMPOUND	Sumitomo EME-G770HT
LEAD FINISH	Matte Sn

3. QUALIFICATION ITEMS, TEST CONDITION AND FLOW:


3-1. QUALIFICATION ITEMS:

Test Item	Reference	Test Condition
1. Heat Resistance Test: Reflow Test	JEDEC J-STD-020	MSL: Follow JEDEC MSL Level 3 (30°C/60%RH, 192hrs)
2. Pressure Cooker Test	JESD22-A102	121 °C/ 100%RH/2 atm
3. Temperature Cycling Test	JESD22-A104	-65 °C - 150 °C
4. Highly Accelerated Temperature and Humidity Stress Test	JESD22-A110	130 °C / 85% RH
5. Solderability Test	JESD22-B102	<ul style="list-style-type: none"> ■ Steam aging 8hrs & Dipping Time \leq 5sec ■ Sn-Ag-Cu solder paste: 245°C ■ Sn-Pb solder paste: 235 °C

*Perform SAT examination before and after Preconditioning per JESD22-A112.




3-2. HEAT RESISTANT TEST (REFLOW TEST) AND RELIABILITY TEST FLOW





MACRONIX INTERNATIONAL CO., LTD.
旺宏電子股份有限公司

3-2-1. REFLOW PROFILE:



Note 1: Subject the samples to 3 cycles of the above defined reflow conditions

Note 2: Time 25°C to peak temperature: 8 minutes max.

Note 3: The time between reflows shall be 5 minutes minimum and 40 minutes maximum.

3-2-2. CRITERIA:


LTPD= 3%, PCT 96 hours and TCT 500 cycles & HAST 96 hours.

3-2-3. REFERENCE SPECIFICATION:

5650-0901: ASSEMBLY RELIABILITY QUALIFICATION SPEC



3-3. SOLDERABILITY TEST FLOW





MACRONIX INTERNATIONAL Co., LTD.
旺宏電子股份有限公司

4. RESULTS:

4-1. HEAT RESISTANCE TEST and RELIABILITY TEST RESULTS:

PRODUCT	6646E		
LOT#	3B777600A5-1	3B777600A5-2	3B777600A5-3
DATE CODE	L0939	L0939	L0940
SAT 1	0/22	0/22	0/22
PRECON	0/250	0/250	0/250
SAT 2	0/22	0/22	0/22
PCT 96 HRS	0/77	0/77	0/77
TCT 500 CYC	0/77	0/77	0/77
HAST 96 HRS	0/77	0/77	0/77

FAIL / SAMPLE SIZE

4-2. SOLDERABILITY TEST RESULTS:

Matte Sn Plating

Plating Material	Matte Sn		
Solder Paste Material	Sn-(3.0-4.0)Ag-0.5Cu		
INSPECTION	0/5	0/5	0/5

FAIL / SAMPLE SIZE

Plating Material	Matte Sn		
Solder Paste Material	63Sn-37Pb		
INSPECTION	0/5	0/5	0/5

FAIL / SAMPLE SIZE

5. CONCLUSION: PASS







MACRONIX INTERNATIONAL CO., LTD.
旺宏電子股份有限公司

6. ATTACHED FILE:

6-1. SAT PHOTO

6-1-1. BEFORE PRE-CONDITION

<p>a1. Lot: 3B777600A5-1: Topside of package</p> 	<p>a2. Lot: 3B777600A5-1: Through Scan View</p> 
<p>b1. Lot: 3B777600A5-2: Topside of package</p> 	<p>b2. Lot: 3B777600A5-2: Through Scan View</p> 
<p>c1. Lot: 3B777600A5-3: Topside of package</p>	<p>c2. Lot: 3B777600A5-2: Through Scan View</p>




6-1-2. AFTER PRE-CONDITION


a1. Lot: 3B777600A5-1: Topside of package




a2. Lot: 3B777600A5-1: Through Scan View



b1. Lot: 3B777600A5-2: Topside of package



b2. Lot: 3B777600A5-2: Through Scan View



c1. Lot: 3B777600A5-3: Topside of package

c2. Lot: 3B777600A5-3: Through Scan View

